

AUTO PPF Super



INTRO

The AUTO brand, exclusively from Spandex, is designed to cater for the ever-changing needs of professional wrappers, detailers and fleet applicators. The products are co-branded and have been developed in conjunction with leading manufacturers. Auto offers a range of special edition automotive colours, paint protection films, automotive tint films and accessories. The Auto PPF range has been manufactured by Orafol exclusively for Spandex.

PRODUCT DESCRIPTION

Customized Top-coated polyurethane film, transparent, glossy with excellent UV resistance and a self-healing surface. The surface is highly resistant to chemicals. The migration of dirt into the film is effectively prevented by the surface coating, which prevents yellowing.

TOPCOAT

Self-healing properties with excellent stain retention, highest chemical resistance; Hydrophobic; No cap-sheet for best plotter usage.

FILM

Thermoplastic Polyurethane with high impact resistance, stone chip protection, highly transparent and high UV resistance with excellent cutting quality.

ADHESIVE

Solvent polyacrylate, permanent with high initial tack, highly transparent, high UV resistance and non yellowing properties.

RELEASE LINER

Matt PET, 75 µm, siliconized on one side.

AREA OF USE

The market for Paint Protection Films (PPF) is one of fastest growing within vehicle wrapping and customization. PPF are technologically advanced, specialist films that offer paint protection against scratches and marks. The desire to protect and customize vehicles with PPF presents a new opportunity for detailers and vehicle wrappers to expand their existing offering.

AUTO PPF Super is designed for the protection of sensitive surfaces against particularly strong mechanical forces in interior and exterior applications. Specially developed for the protection of car-paints e.g. front and rear bumpers and side skirts against stone chipping, scratches. Recommended for bonding to even and slightly curved surfaces.

Technical Data

Thickness ⁽¹⁾	205 micron (incl. adhesive)
Dimensional stability ⁽¹⁾ (FINAT TM 14)	Adhered to steel, shrinkage 0,2 mm max.
Temperature resistance ⁽²⁾	Adhered to aluminium, -40°C to +100°C, no variation
Resistance to solvents and chemicals Immerse for 1 hour (water, acid), 30 Min (Pancreatine, tree gum), 10 Min (IPA,Gasoline, Motor oil), Check after 24h at RT	No Detrimental Effect on: Water, Sulfuric Acid (10%), Hydrochloric Acid (10%), Bird droppings (Pancreatine), Tree gum, Gasoline, Motor oil, Isopropanol
Aging Test Xenon weathering acc. To DIN EN ISO 4892	> 1000 hr No Detrimental Effect
Gravel Resistance SAE J400 2.4L of Gravel	Pass
Gloss level Determined at 20° angle	>96 (GU)
Adhesive power ⁽¹⁾ (FINAT TM 1, 180°, after 24h stainless steel)	17 N/25 mm
Tensile strength (DIN EN ISO 527)	Along: min. 29 MPa; Across: min. 29 MPa
Elongation at break (DIN EN ISO 527)	Along: min. 300%; Across: min. 300%
Shelf life ⁽³⁾	2 years
Application temperature	> +10°C
Proposed application technique	Wet application process using f. eg. ORAFOL® Application Gel
Available width	152,0 cm
Maximum service life by specialist application Applies for vertical outdoor exposure ⁽⁴⁾	10 years

(1) average (2) short-time exposure (3) in original packaging, at 20° C and 50% relative humidity (4) normal climate of Central Europe

PREPARATION GUIDELINE:

- The better the preparation the better the result
- Conventional cleaning agents and cleaning clay
- No substances that form a coating or sealing layer by nanotechnology
- Remove all residues of preservative wax or polishing agents
- Finally, all surfaces must always be cleaned with Pre-Wrap Surface Cleaner
- Thoroughly dry the vehicle – especially under rubber seals



APPLICATION GUIDELINE:

- Clean and dust free room, preferably with car lift or mounting ramp
- Minimum temperature +18 °C ☒ rapid evaporation of residual moisture
- We recommend only wet application
- Use f. eg. ORAFOL Application Gel
- Mixing is possible:
Water → reduces viscosity
Isopropanol/water mixtures → initiates more tack to adhesive
(CAUTION: mixing is exothermic!)
- Spray to open adhesive side and surface to be covered
- Best applied with spray bottle
- Dries off residual-free
- Push the squeegee gently from the middle to the side with big overlaps
- Remove excessive gel with water and lint free cloth
- Prolonged slip-behaviour ☒ repositionability of the film
- Adhesion builds up smoothly ☒ reduces risk of lift lines and air entrapments.
- Do not heat up TPU films too much – need much less temperature.
- Any cloudiness of the adhesive disappears within 3-5 days

MAINTENANCE GUIDELINE:

- 3 days after application: cleaning in car wash is possible
- No high pressure cleaning recommended
- Contaminants such as bird droppings and tar that can cause fatal damage to the paint can also cause considerable damage to the PPF, so please remove them as soon as possible
- For Long-Lasting film properties we recommend to use regularly f. e.g. ORAFOL PPF Cleaning and Care

REMOVABILITY GUIDELINE:

- Removal of the film at least 20°C temperature
- Angle 180 °
- Hot air blower helps

APPLICATION TRAINING:

Training & education is the key to success a perfect PPF installation. Spandex offers regular training for customers interested in PPF applications. Please contact your local Spandex for more information.

NOTE: Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. We recommend wet application of the film. Furthermore, the application information published by AUTO must be considered.

IMPORTANT NOTICE: All AUTO products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning AUTO products is based upon research which the company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of AUTO products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

DISCLAIMER GENERAL: Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of such products for their specific use, including, but not limited to, the application, conditions, maintenance, and the Purchaser shall assume all risk and liability of every nature in connection therewith. All technical data are subject to change without prior notice. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading. Spandex gives no express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of fitness for any particular use and/or non-infringement. All products are sold subject to Spandex's general terms and conditions of sale. Spandex's aggregate liability, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoiced to Purchaser in respect of any occurrence or series of occurrences. In the event of improper use and/or incorrect processing that does not comply with our instructions, any and all liability is excluded. In no circumstances shall Spandex be liable for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.